



Miragrid[®] 20XT

Miragrid[®] 20XT geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Miragrid[®] 20XT geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Miragrid[®] 20XT geogrid is used as soil reinforcement in MSE structures such as; segmental retaining walls, precast modular block walls, wire faced walls, geosynthetic wrapped faced walls and steepened slopes. Miragrid[®] 20XT is also used in MSE stabilized platforms for voids bridging, embankments on soft soils, landfill veneer stability, reducing differential settlement and for foundation seismic stability.

TenCate Geosynthetics Americas is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

Mechanical Properties	Test Method	Unit	Machine Direction Value
Tensile Strength @ Ultimate (MARV ¹)	ASTM D6637 (Method B)	lbs/ft (kN/m)	13705 (200.0)
Tensile Strength @ 5% strain (MARV ¹)	ASTM D6637 (Method B)	lbs/ft (kN/m)	5340 (77.9)
Creep Rupture Strength ²	ASTM D5262/D6992	lbs/ft (kN/m)	9452 (137.9)
Long Term Design Strength ³		lbs/ft (kN/m)	7540 (110.0)

¹ Minimum Average Roll Values (MARV) shown above are based on QC Testing per a defined lot not to exceed 12 months. Testing Frequency follows ASTM D4354, Table 1.

² 75-year design life based on NTPEP Report [REGEO-2011-01-001](#) and [REGEO-2015-01-002](#).

³ Long Term Design Strength for Type 3 Backfill (Silty Sand), 6-inch lift / 25,000-lb roller. $RF_{CR} = 1.45$; $RF_{ID} = 1.09$; $RF_D = 1.15$ (Installation damage reduction factor for other soils available upon request).

Physical Properties	Unit	Roll Characteristic
Mass/Unit Area (ASTM D5261)	oz/yd ² (g/m ²)	19.6 (664)
Roll Dimensions ⁴ (width x length)	ft (m)	12 x 200 (3.6 x 61) 12 x 1000 (3.6 x 305)
Roll Area	yd ² (m ²)	267 (220) 1333 (1114)
Estimated Roll Weight	lbs (kg)	360 (163) 1725 (781)

⁴ Special order roll lengths are available upon request.

Miragrid 20XT and Tensile Strength direction are continuously printed in white on the edge of the roll.

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Miragrid[®] is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

DX2 Geosyntex, Inc.
307 Industrial Park Dr., Lawrenceville, GA 30046
770-682-1758
www.dx2.net

